


| | | | |
|----------------------------------|---------|-------|----------|
| Initial permeability | μ_i | 25°C | 3200±25% |
| Saturation magnetic flux density | Bs(mT) | 25°C | 530 |
| | | 100°C | 420 |
| Remanence | Br(mT) | 25°C | 130 |
| | | 100°C | 80 |
| Coercivity | Hc(A/m) | 25°C | 11 |
| | | 100°C | 10 |
| | | 25°C | 350 |



| | |
|-----------------------|-------------------|
| $\rho(\Omega\cdot m)$ | 3 |
| d(kg/m³) | 4.8×10^3 |

| | |
|------------------------|------|
| Curie temperature | 45°C |
| Electrical resistivity | |
| Density | |



| | |
|------------------------|--|
| Test core : Toroid(mm) | |
| OD : 25 | |
| ID : 15 | |
| H : 7.5 | |

