


Bs-Temperature


H=1194A/m

Initial permeability	μ_i	25°C	1500±25%
Saturation magnetic flux density	B_s (mT)	25°C	410
Remanence	B_r (mT)	25°C	210
Coercivity	H_c (A/m)	25°C	24
Core loss	P_{cv} (kW/m³)	25°C	1000
Core loss	100kHz 200mT	100°C	480
Curie temperature	T_c (°C)	≥285	
Electrical resistivity	ρ (Ω·m)	3	
Density	d (kg/m³)	4.8×10³	




Dimensions (mm):
 5
 5
 5

μ_i -Temperature



Core dimensions:
 OD : 21
 ID : 11
 H : 7

B-H



μ_i -Frequency

