



Initial permeability	μ_i	25°C	3300±25%
Saturation magnetic flux density	B_s (mT)	25°C	530
		100°C	410
Remanence	B_r (mT)	25°C	80
		100°C	60
Coercivity	H_c (A/m)	25°C	10
		100°C	8
Core loss	P_{cv} (kW/m ³)	25°C	34
		80°C	26



